

# Sample

고객명: 코스모텍

모델명: COS-294-B0 T2



No	μm		Au	tolerance		
	Au	Ni		0.133	0.161	0.189
1	0.176	3.702	OK			
2	0.168	3.648	OK			
3	0.184	3.810	OK			
4	0.166	3.659	OK			
5	0.183	3.683	OK			
6	0.152	3.717	OK			
7	0.133	3.545	OK			
8	0.161	3.956	OK			
9	0.140	3.670	OK			
10	0.148	3.625	OK			
Mean	0.161	3.702				
S.Dev	0.018	0.112				

FUNC: MEASURE  
DATE: 2013-03-08  
TIME: 오전 11:23:45  
COL : 0.10 mm

Au  
Ni  
Cu

SEC : 30 Sec

Total judge : OK



도금원소 : 1 %Au/Ni//Cu  
측정값 개수    10    10  
최대값        0.184 3.956  
최소값        0.133 3.545  
범위            0.051 0.411  
평균값        0.161 3.702  
표준편차      0.018 0.112  
변동계수      10.923 3.029

