

Sample

顧客:(株)コスモテック

モデル: COS-294-B0 T2



No	μm	μm	Au	tolerance		
	Au	Ni		0.133	0.161	0.189
1	0.176	3.702	OK			
2	0.168	3.648	OK			
3	0.184	3.810	OK			
4	0.166	3.659	OK			
5	0.183	3.683	OK			
6	0.152	3.717	OK			
7	0.133	3.545	OK			
8	0.161	3.956	OK			
9	0.140	3.670	OK			
10	0.148	3.625	OK			
Mean	0.161	3.702				
S.Dev	0.018	0.112				

FUNC: MEASURE
DATE: 2013-03-08
TIME: AM 11:23:45
COL: 0.10 mm

Au
Ni
Cu

SEC: 30 Sec

Total judge: OK



メッキ元素: 1 %Au/Ni//Cu
測定数 10 10
最大値 0.184 3.956
最小値 0.133 3.545
範囲 0.051 0.411
平均値 0.161 3.702
標準偏差 0.018 0.112
変動係数 10.923 3.029

